

# High Purity Sanitary Stainless Steel Tubing ASTM A270-S2 BPE

Tuyauterie en acier inoxydable à haut degré de pureté ASTM A270-S2 BPE

## ASTM Chemical Composition Requirements (Max.)

| Element<br><i>élément</i> | T316L<br>(EN 1.4404/UNS S31603) |
|---------------------------|---------------------------------|
| (C) Carbon, max.          | 0.030                           |
| (Mn) Manganese, max.      | 2.000                           |
| (P) Phosphorus, max.      | 0.045                           |
| (S) Sulphur, max.         | 0.030                           |
| (S) Sulphur, A270-S2      | 0.005-0.017                     |
| (Si) Silicon, max.        | 0.750                           |
| (Ni) Nickel               | 10.0-14.0                       |
| (Cr) Chromium             | 16.0-18.0                       |
| (Mo) Molybdenum           | 2.0-3.0                         |



### RODGER INDUSTRIES INC.

P.O. BOX 40  
8913 Talbot Trail  
Blenheim, Ontario  
CANADA N0P 1A0

 +1 (519) 676-3244

 +1 (519) 676-4955

 [www.rodgerindustries.com](http://www.rodgerindustries.com)

 [info@rodgerindustries.com](mailto:info@rodgerindustries.com)