

General Service Stainless Steel Tubing ASTM A269

Tuyauterie Tout Usage ASTM A269

ASTM Chemical Composition Requirements (Max.)

Element <i>élément</i>	T304L	T316L
(C) Carbon, max.	0.030	0.030
(Mn) Manganese, max.	2.000	2.000
(P) Phosphorus, max.	0.045	0.045
(S) Sulphur, max.	0.030	0.030
(Si) Silicon, max.	0.750	0.750
(Ni) Nickel	8.0-12.0	10.0-14.0
(Cr) Chromium	18.0-20.0	16.0-18.0



RODGER INDUSTRIES INC.

P.O. BOX 40
8913 Talbot Trail
Blenheim, Ontario
CANADA N0P 1A0

 +1 (519) 676-3244

 +1 (519) 676-4955

 www.rodgerindustries.com

 info@rodgerindustries.com